

TECHNICAL INFORMATION

HS Akzent 100 Wax



HighSolid oil/wax basing on natural ingredients. Accentuates the natural character of the wood.

- Even, rich surface appearance
- 100% solid - solvent-free
- Extremely economical to use
- Increases the surface's water resistance

Range of use:


Suitable for the final treatment of hardwood floors that has been impregnated with HS Akzent 100 Oil.



Technical Data

Art.-no.

10602



Solids contents	99.7 ±2%
Storage and transportation	modified vegetable oils, vegetable waxes, waxes, lead-free siccatives
Storage and transportation	36 months of storage stability. No hazardous material according to ADR. Not sensitive to frost.
GISCODE	Ö10+

Application

- The surface must be sanded properly, wood moisture content max. 12%.
- The floor must be dry and free from any old coatings, oil, grease, wax, silicone, sanding dust and other contaminants. Room temperature +15°C to +25°C, relative humidity 40% to 75%, material temperature +18°C to +25°C. Ensure working areas are adequately ventilated.
- Observe the general and, if available, the product-specific health and safety instructions. More specific information relating to GISCODE can be found in the usage instructions, which are available at www.wingis-online.de.

2/2016



TECHNICAL INFORMATION

HS Akzent 100 Wax



Application

Thinner

The product is supplied ready for use and must not be diluted!

Application tool/application rate

LOBATOOL trowel / 10-20ml/m² (50-100m²/l) depending on the absorbency of the substrate. Equalise with LOBATOOL special pad in beige or white.

Drying time

- Can be walked on after 12 hours.
- Usable after 24 hours.
- Coverage after 10 days.
- The floor can be covered earlier by using LOBATOOL Cover 400, for details see the TI for the product.

Preparation:

- Apply LOBASOL® HS Akzent 100 Oil in sections using a LOBATOOL trowel.
- Immediately equalise with the single-disc machine and the LOBATOOL special pad in beige underneath.
- Dry overnight.

Processing:

- HS Akzent 100 Wax is applied in sections using a LOBATOOL flat metal trowel.
- Immediately equalise with the single-disc machine and the LOBATOOL special pad in beige or white underneath.

Important information

Excess material must be completely removed during equalisation. Drying delays are possible on some exotic timbers. Keep soaked cloths, pads and other tools in closed containers. Moisten oil in combination with sanding dust, fabric cloths and so on with water or store in a sealable bucket and dispose of in a fire-safe manner, since otherwise there is a risk of self-ignition.

Trowel applications are only possible with joint-sealed wooden flooring. Oil that penetrates joints will not dry completely over a long period.



TECHNICAL INFORMATION

HS Akzent 100 Wax



General guidelines

Cleaning of tools: Clean tools with solvents such as brush cleaner.

Drying time: The indicated drying times are valid for +20°C and 55% to 65% relative humidity, and assume careful, draught-free ventilation of the working area. Lower temperatures, higher relative humidity or poorer ventilation lead to longer drying times. Do not apply any protective coverings, wet clean the surface or lay carpet until the coating has achieved its final hardening. Product-specific data can be found in the relevant technical information.

Side bonding: Parquet that has not been shear-resistantly bonded in place, wood planks, wooden pavings, industrial parquet and parquet on underfloor heating as well as types of wood with a short moisture changing times (e.g. beech) show dimensional changes caused by quickly varying climate (rel. air humidity, temperature). When applying oil side bonding and thus unregular cracks in joints can not appear.

Interactions: Materials such as carpet underlays, furniture legs, castors, flexible adhesives used for parquet or for fixing can lead to softening and discolouration. Material building up in the joints can adversely affect touch and appearance. Exposure to hair dyes or rubber tyres on cars, motorcycles and cycles can lead to permanent, irreversible discolouration of the surface.

The information in this document and all other advice and recommendations that we provide to help and assist the applicator are based on previous experience and relate to normal conditions. Because of the wide range of possible uses and conditions of application of our products, we do not relieve users from the need to carry out their own trials or to seek technical advice by speaking to the LOBA application engineering department. Observe the floor covering manufacturer's recommendations and the provisions of the current standards. Our liabilities and responsibilities are exclusively in accordance with our Terms and Conditions and are not extended by this information or by our advice. The publishing of a new technical data sheet automatically invalidates the earlier version.

2/2016

